

TÜV Rheinland LGA Products GmbH · 51101 Cologne
OOO «Egida +»
Gulnara Yakhina
Krasnokokshayskaya Ul. 47
420032 Kazan
RUSSIAN FEDERATION

Contact
E-Mail
Phone
Fax
Cologne,

Petra Van Dyck
Petra.Van.Dyck@de.tuv.com
+49 221/806-2129
+49 221/806-2882
18.05.2018

Report No. 0003251792/30 AZ 301178

Test item: One Foam

Identification: Article name: Flexible foam
Article no.: VE5014
Supplier name and number: "Egida+" ltd.
Date stamp of article: 18 April 2018
Material / Component: Polyurethane
Manufacturer's name: "Egida+" ltd.

Condition at delivery: No claim

Date of delivery: 07.05.2018

Place of testing: Cologne

Test period: 15.05.2018 to 18.05.2018

Test scope: Parameters selected by customer

Test specification: IKEA IOS-MAT-0010 Vers. AA-10911-13 dated 2015-11-13

Test result: Pass - According to the kind and extent of tests performed the test item meets the test specification.

Cologne, 18.05.2018

X 

Sachverständige(r)/Expert
Signiert von: Gunther Bier

X 

Sachverständige(r)/Expert
Signiert von: Petra Van Dyck

Report No.: 0003251792/30 AZ 301178
Date: 18.05.2018

1. Results

Organotin compounds

Sample No.	301178-002		
Sample composition	Art. 1		
Unit	mg/kg		
Organotin compounds, total	n.n.		
Monobutyltin, MBT	<0,005		
Dibutyltin, DBT	<0,005		
Tributyltin, TBT	<0,005		
Tetrabutyltin, TeBT	<0,005		
Monooctyltin, MOT	<0,005		
Diocetyl tin, DOT	<0,005		
Tricyclohexyltin, TcyT	<0,005		
Triphenyltin, TPHT	<0,005		
Di-n-propyl tin	<0,005		
Diphenyl tin	<0,005		

Limit values:
DBT and TBT 0,2 mg/kg each
Sum of all organotin compounds 2,5 mg/kg

Plasticizer

Sample No.	301178-003		
Sample composition	Art. 1		
Unit	mg/kg		
Phthalates			
Bis-(2-ethylhexyl)phthalate, DEHP	<50		
Dibutylphthalate, DBP	<50		
Benzylbutylphthalate, BBP	<50		
Diisononylphthalate, DINP	<50		
Diisodecylphthalate, DIDP	<50		
Di-n-octylphthalate, DNOP	<50		
Diisobutylphthalate, DIBP	<50		
1,2-Benzenedicarboxylic acid, di-C6 -8-branched alkyl esters, C7-rich, DIHP	<50		
Bis-(2-methoxyethyl) phthalate, BMEP	<50		
Di-n-hexyl phthalate, DNHP	<50		
1,2-benzenedicarboxylic acid, di-C7-11-branched and linear alkyl ester, DHNUP	<50		
Diisopentylphthalate DiPP	<50		
n-Pentyl-isopentyl phthalate, PiPP	n.n.		
Diisohexyl phthalate	n.n.		
1,2-benzenedicarboxylic acid, dipentylester, branched and linear	<50		
Di-n-pentylphthalate, DnPP	<50		
Dipentyl phthalate ester	<50		
Di-C6-C10-Phthalate-ester	<50		
Dicyclohexylphthalate, DCHP	n.n.		

Limit values:
100 mg/kg for each phthalate

Report No.: 0003251792/30 AZ 301178
Date: 18.05.2018

TDA and MDA

Sample No.	301178-001		
Sample composition	Art. 1		
Unit	mg/kg		
2,4-Toluyldiamine	<1		
2,6-Toluyldiamine	<1		
2,2-Diaminodiphenylmethane	<1		
2,4-Diaminodiphenylmethane	<1		
4,4'-Diaminodiphenylmethane	<1		

Limit value 5 mg/kg per compound

Report No.: 0003251792/30 AZ 301178
Date: 18.05.2018

2. Summary of methods

Organotin compounds		
----------------------------	--	--

Method description: In-house method - Determination of organotin compounds after extraction with methanolic solvent and derivatisation. Quantification by GC-MS
Notes: Quantification equates the DIN EN ISO 17353.

Plasticizer		
--------------------	--	--

Method description: In-house method - Determination of selected phthalates after solvent extraction, quantification by GC-MS
Notes: Quantification equates the DIN EN ISO 18856.

TDA and MDA		
--------------------	--	--

Method description: Determination of TDA and MDA after extraction with 0,1% acetic acid, afterwards derivatization with pentafluoropropionic acid anhydride (PFPA) and quantification by LC-MS according to Analytica Chimica Acta 510 (2004) 109-119, deviation in sample preparation 0,4 g on 6 ml

----End of report----